

NEOPRENE/EPT/SBR

Product Code			R421	R426	R427	R428
PROPERTY	TEST METHOD	UNITS		*R426	*R427	*R428
Density	ASTM D 1056	PCF	8 - 12	5 - 7	6 - 8	8 - 10
Compression Deflection (25%)	ASTM D 1056	PSI	2 - 5	2 - 5	5 - 9	9 - 13
C/D Heat Aging (7 days @158 F)	ASTM D 1056	% MAX CHG	30	30	30	30
Shore OO Durometer			25 - 45	35 - 55	45 - 60	50 - 65
Compression Set (1) (50%)	ASTM D 1056	% MAX	40	50	50	50
Tensile	ASTM D 412	PSI MIN	50	25	40	60
Elongation	ASTM D 412	% MIN	150	125	90	90
Fluid Immersion (2)	ASTM D 1056	WT % MAX				
Water Absorption	ASTM D 1056	WT % MAX	5	10	5	5
	ASTM D 1667	LBS/SQ FT	0.1	0.1	0.1	0.1
Linear Shrinkage (7 days @ 158 F)	ASTM C 534	% MAX	5	10	10	10
Ozone Resistance (72 hours @ 50 ppm)	ASTM D 1171	RATING	0	0	0	0
Thermal Conductivity (3)	ASTM C 177					
Bashore (% Rebound Average)						
Resiliance (1/2" thickness @ 72 F)			30 - 40	20 - 45	20 - 45	20 - 45
Temperature Use: Cold Crack	ASTM D 1056	°F	-70	-70	-70	-40
High (10)		°F	200	200	200	200
Flammability Rating (4)	FMVSS302		PASS	PASS	PASS	PASS
	U.L. 94*		LISTED	LISTED	LISTED	LISTED
Sheet Size	+/-3%	INCHES	42 x 60	42 x 72	42 x 72	42 x 60
Expected Yield (11) Thickness		INCHES	2.25	2.5	2.25	2.0
Specifications	ASTM D 1056-67		SCE41	SCE41	SCE42	SCE43
	ASTM D 1056-98		2A1	2A1	2A2	2A3
	Mil R 6130 Type 2 Grade		BorC SOFT			
Special Orders (7)						
Colors			BLK	BLK	BLK	BLK

*Denotes FR Grades

IR Specialty Foam and Packaging cannot predict or control the different conditions under which this information and our products may be applied. Therefore, we do not guarantee the applicability, the suitability of our foams, nor the accuracy of this information. There is no warranty either expressed or implied on our products. Buyer assumes all responsibility for loss or damage arising from the use of our products, whether done in accordance with directions or not. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patents. Users of our products should perform testing to determine their efficiency and suitability prior to use.