

## A1225

FOAM GRADE: **P120-25N7**  
COLOR: WHITE  
CARDIO

EFFECTIVE: 03-01-00  
SUPERSEDES: 11-01-99

TEST ITEM	UNIT	LIMITS	TEST METHOD
DENSITY	PCF	1.15-1.25	ASTM 3574
I.F.D. @ 4" THICK			
- 25% DEFLECTION	LBS.	22 TO 28	ASTM 3574
- 65% DEFLECTION	LBS.	38.5 MIN.	ASTM 3574
SUPPORT FACTOR	RATIO	1.75 MIN.	
RECOVERY	%	N/A	
HYSTERESIS LOSS	%	N/A	
COMPRESSION FORCE DEFLECTION	LBS.		
CONSTANT DEFLECTION COMPRESSION SET			
- 90% DEFLECTION	%	10.0 MAX.	ASTM 3574
- 50% DEFLECTION	%	5.0 MAX.	ASTM 3574
STEAM AUTOCLAVE AGING			
- COMPRESSION SET @ 50% DEFLECTION	%	N/A	ASTM 3574
- C. F. D. LOSS @ 50%	%	N/A	
DRY HEAT AGING			
- COMPRESSION SET @ 50% DEFLECTION	%	N/A	ASTM 3574
- C. F. D. LOSS @ 50%	%	N/A	
AIR FLOW	CFM	4.0 MIN.	ASTM 1564
RESILIENCE (BALL TEST)	%	50.0 MIN.	ASTM 3574
TENSION TEST			
- TENSILE STRENGTH	PSI	10.0 MIN.	ASTM 3574
- ULTIMATE ELONGATION		150 MIN.	ASTM 3574
GRIP SEPARATION	%		
TEAR RESISTANCE	PLI	1.25 MIN.	ASTM 3574
STATIC FATIGUE 75%			
- I. F. D. LOSS @ 25%	%	N/A	ASTM 3574
- THICKNESS LOSS @ 75% COMPRESSION	%	N/A	ASTM 3574