

A1550 Char

FOAM GRADE: **P145-50E1**
COLOR: GREY
ANTIMICROBIAL TREATED

EFFECTIVE: 03-01-00
SUPERSEDES: 11-01-99

TEST ITEM	UNIT	LIMITS	TEST METHOD
DENSITY	PCF	1.40-1.50	ASTM 3574
I.F.D. @ 4" THICK			
- 25% DEFLECTION	LBS.	45.0-55.0	ASTM 3574
- 65% DEFLECTION	LBS.	81.0 MIN.	ASTM 3574
SUPPORT FACTOR	RATIO	1.80 MIN.	
RECOVERY	%		
HYSTERESIS LOSS	%	N/A	
COMPRESSION FORCE DEFLECTION	LBS.	N/A	
CONSTANT DEFLECTION COMPRESSION SET			
- 90% DEFLECTION	%	10.0 MAX.	ASTM 3574
- 50% DEFLECTION	%	5.0 MAX.	ASTM 3574
STEAM AUTOCLAVE AGING			
- COMPRESSION SET @ 50% DEFLECTION	%	N/A	
- C. F. D. LOSS @ 50%	%		
DRY HEAT AGING			
- COMPRESSION SET @ 50% DEFLECTION	%	N/A	
- C. F. D. LOSS @ 50%	%		
AIR FLOW	CFM	2.0 MIN.	ASTM 1564
RESILIENCE (BALL TEST)	%	40.0 MIN.	ASTM 3574
TENSION TEST			
- TENSILE STRENGTH	PSI	10.0 MIN.	ASTM 3574
- ULTIMATE ELONGATION GRIP SEPARATION	%	100 MIN.	ASTM 3574
TEAR RESISTANCE	PLI	1.20 MIN.	ASTM 3574
STATIC FATIGUE 75%			
- I. F. D. LOSS @ 25%	%		
- THICKNESS LOSS @ 75% COMPRESSION	%		

THIS PRODUCT HAS BEEN MANUFACTURED WITH AN ANTIMICROBIAL AGENT (BIO-PRUF) TO RESIST THE GROWTH OF MOLD, MILDEW AND ODOR CAUSING GERMS THAT CAN LEAD TO PREMATURE PRODUCT FAILURE.

FOAMEX MAKES NO WARRANTY EXPRESS OR IMPLIED, EXCEPT THAT SUCH POLYURETHANE FOAM PRODUCTS MEET OR EXCEEDS THE CRITERIA OUTLINED ABOVE AT THE TIME OF SHIPMENT. FOAMEX MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS OF THE GOODS FOR ANY PARTICULAR PURPOSE.

USER SHALL DETERMINE THE APPROPRIATENESS OF THESE MATERIALS FOR INTENDED APPLICATIONS, AND ASSUMES TOTAL LIABILITY REGARDING DAMAGE OR LOSS ARISING FROM THE USE OF THIS PRODUCT.