

B1010

FOAM GRADE: **F100-09C7**
 COLOR: LT. GREY
 CARDIO

EFFECTIVE: 03-01-00
 SUPERSEDES: 11-01-99

TEST ITEM	UNIT	LIMITS	TEST METHOD
DENSITY	PCF	0.90 TO 1.00	ASTM 3574
I.F.D. @ 4" THICK			
- 25% DEFLECTION	LBS.	9 TO 15	ASTM 3574
- 65% DEFLECTION	LBS.	15.3 MIN.	ASTM 3574
SUPPORT FACTOR	RATIO	1.70 MIN.	
RECOVERY	%	85 MIN.	
HYSTERESIS LOSS	%	15% MAX.	
COMPRESSION FORCE DEFLECTION			
	LBS.		
CONSTANT DEFLECTION COMPRESSION SET			
- 90% DEFLECTION	%	10% MAX	ASTM 3574
- 50% DEFLECTION	%	5.0 MAX	ASTM 3574
STEAM AUTOCLAVE AGING			
- COMPRESSION SET @			
50% DEFLECTION	%		ASTM 3574
- C. F. D. LOSS @			
50%	%		
DRY HEAT AGING			
- COMPRESSION SET @			
50% DEFLECTION	%		ASTM 3574
- C. F. D. LOSS @			
50%	%		
AIR FLOW	CFM	4.0 MIN.	ASTM 1564
RESILIENCE (BALL TEST)	%	45% MIN.	ASTM 3574
TENSION TEST			
- TENSILE STRENGTH	PSI	10.0 MIN.	ASTM 3574
- ULTIMATE ELONGATION		180 MIN.	ASTM 3574
GRIP SEPARATION	%		
TEAR RESISTANCE	PLI	1.25 MIN.	ASTM 3574
STATIC FATIGUE 75%			
- F. D. LOSS @ 25%	%	10 MAX	ASTM 3574
- THICKNESS LOSS @ 75% COMPRESSION	%	1 MAX	ASTM 3574

FLAMMABILITY PERFORMANCE *

- CALIFORNIA TECHNICAL BULLETIN 117, SEC. A, PART I PASS
- CALIFORNIA TECHNICAL BULLETIN 117, SEC. D, PART II PASS
- FEDERAL M.V.S.S. 302

* THIS FLAMMABILITY DATA IS NOT INTENDED TO REFLECT HAZARDS PRESENTED BY THIS OR ANY OTHER MATERIAL UNDER ACTUAL FIRE CONDITIONS.