



Foam Grade B2436

(MEETS TEST STANDARD: ASTM - D-3574)

DENSITY, lbs/cu. ft. 2.25 - 2.40

ILD @ 25% , 4" 31 - 37

TEAR STRENGTH, psi 1.25min

TENSILE STRENGTH, psi 14 min

ELONGATION, % 275 - 350

RESILIENCE, % 45 min

COMPRESSION, 90%, 10% max  
22 HOURS, 158 F

#### FLAMMABILITY PERFORMANCE

CAL-117, Sec A, Part I pass

CAL-117, Sec D, Part II pass

MVSS - 302 pass

COLOR Yellow

Foamex certifies to the above specifications

Randy McClellan  
Technical Director